

TECHNICAL DATA SHEET

PremARC™ 219 Tack Latex

Description

PremARC™ 219 Tack Latex is a carboxylated styrene-butadiene emulsion that has a very soft and resilient hand. Due to its styrene content and molecular weight it has found applications in mastics and pressure sensitive adhesives.

Physical Properties

Emulsifiers	Anionic
Bound Styrene	45 %
Viscosity (Brookfield #2/20 rpm)	300 cps
Glass Transition Temp. (Tg)	-16° F(-27° C)
pH	8.7
Solids Content	50.0 %
Particle Diameter	0.14 Microns
Residual Monomer	0.07 % Max

*These are typical properties of the emulsion and should not be considered specifications. Copies of the specifications are available upon request.

Applications

Binder used in running track application for the 1st sprayed tack layer. Product has excellent adhesion to cured asphalt.

Features

- Soft Hand
- Excellent chemical and solvent resistance
- Tough/flexible film properties

Storage and Handling

Protect from freezing. Ideal storage temperature is 72°F(22°C). Stability at 72°F(22°C) is 180 days when properly stored. *Read the PremARC™ 219 Tack Latex Material Safety Data Sheet before handling, storing, or using this product.*

Packaging Form

Available in 275 gallon Corrugated Liquid Totes or 55 gallon non-returnable drums.

Customer Notice

ARC encourages its customers to review their application of ARC products from the standpoint of human health and environmental quality. To help ensure that ARC products are not used in ways for which they were not intended or tested, ARC personnel will assist customers in dealing with ecological and products safety. Your ARC sales representative can arrange the proper contacts.

10/23/2017

NOTICE: The information and data contained herein do not constitute sales specifications. The product properties may be changed without notice. No liability, warranty or guarantee of product performance is created by this document. It is the Buyer's responsibility to determine whether ARC products are appropriate for Buyer's use and to ensure that Buyer's workplace and disposal practices are in compliance with applicable laws and regulations. No freedom from any patents owned by ARC or other industrial or intellectual property rights is granted or to be inferred.



American Recycling Center, Inc

655 Wabasse Drive, Owosso, MI 48867
(989) 725-5100 www.americanrecycling.com